



Queensland Magnesia Pty Ltd
ABN 43 010 823 588

QMAG[®] EFH2



Chemical Analysis

	Typical %
MgO	96.5
SiO ₂	0.80
CaO	2.40
Al ₂ O ₃	0.08
Fe ₂ O ₃	0.12
Mn ₃ O ₄	0.12

Physical Properties

	Typical
Bulk Specific Gravity	3.50 g/cm ³
Mean Periclase Crystal Size	700 µm

Available Sizes

0-45mm
0-1mm
1-3mm
3-5mm

Product Description

QMAG[®] EFH2 is electrofused natural magnesite manufactured from Queensland Magnesia's high quality cryptocrystalline magnesite deposit. **QMAG[®] EFH2** is characterised by a high MgO content combined with predominantly dicalcium silicate around the periclase crystal boundaries. This refractory secondary phase combined with large periclase crystal size ensures suitability for use in slag contact areas for steelmaking applications.

Typical Uses

- MgO-C Brick for steelmaking applications
- MgO-Doloma brick
- Other arduous high temperature applications

Typical Packaging

- QMAG[®] EFH2** is available:
- Bulk loose in container or truck

Product Storage

Store in a cool, dry ventilated area.

Queensland Magnesia Pty Ltd

9 Sherwood Road
Toowong, Queensland 4066
AUSTRALIA

Telephone: +61 7 3331 3400
Email: cbougoure@qmag.com.au

Australia and New Zealand
Americas
Japan, India and Malaysia
Africa (CCM only)

QMAG Europe GmbH

Koenigstrasse 84-96
23552 Lübeck
GERMANY

Telephone: +49 451 2927 4250
Email: gmw@qmag.com.au

Europe
Middle East
Africa (DBM and EFM only)

QMAG (Shanghai) Trading Co., Ltd.

Suite 2408-10 CITIC Square
1168 Nanjing West Road Shanghai 200041
CHINA

Telephone: +86 21 5292 5210
Email: brucexu@qmag.com.au

Asia (excl Japan, India and Malaysia)



Quality
ISO 9001



This data contains typical properties only and should not be used for specification purposes. Refer to MSDS Electrofused Magnesite

Ref No: EFH2 – R30
Date Of Issue: 30 March 2009