



Queensland Magnesia Pty Ltd  
ABN 43 010 823 588

# EMAG<sup>®</sup> 3220



## Chemical Analysis

	Typical %
MgO (by difference)	85
SiO <sub>2</sub>	2.5
MgO+CaO	97
Al <sub>2</sub> O <sub>3</sub>	0.25
Fe <sub>2</sub> O <sub>3</sub>	0.25
Mn <sub>3</sub> O <sub>4</sub>	0.1

## Physical Properties

Sizing	Typical %
-1 mm	5
+20 mm	10

## Product Description

**EMAG<sup>®</sup> 3220** is calcined natural magnesium oxide manufactured from Queensland Magnesia's high quality cryptocrystalline magnesite deposit. **EMAG<sup>®</sup> 3220** is a pale pink, granular magnesium oxide, characterised by high levels of combined magnesia and lime with low impurity levels.

## Typical Uses

- Slag conditioner in ferrous and non-ferrous applications

## Typical Packaging

**EMAG<sup>®</sup> 3220** is available:

- Bulk containers

## Product Storage

Store in a cool, dry ventilated area.

### Queensland Magnesia Pty Ltd

9 Sherwood Road  
Toowong, Queensland 4066  
AUSTRALIA

Telephone: +61 7 3331 3400  
Email: [cbouquoure@qmag.com.au](mailto:cbouquoure@qmag.com.au)

Australia and New Zealand  
Americas  
Japan, India and Malaysia  
Africa (CCM only)

### Q MAG Europe GmbH

Koenigstrasse 84-96  
23552 Lübeck  
GERMANY

Telephone: +49 451 2927 4250  
Email: [gmw@qmag.com.au](mailto:gmw@qmag.com.au)

Europe  
Middle East  
Africa (DBM and EFM only)

### Q MAG (Shanghai) Trading Co., Ltd.

Suite 2408-10 CITIC Square  
1168 Nanjing West Road Shanghai 200041  
CHINA

Telephone: +86 21 5292 5210  
Email: [brucexu@qmag.com.au](mailto:brucexu@qmag.com.au)

Asia (excl Japan, India and Malaysia)



This data contains typical properties only and should not be used for specification purposes. Refer to MSDS for Caustic Calcined Magnesia.